

SPECIFICATION AMENDMENTS

In response to the Examiner's objection to informalities on page 8 to correct the name of trade marked products, replace Table II with the following Table:

TABLE II

<u>Metal Service</u>	<u>Recommended CPC(s)</u>
All structural metals including all metals listed in Table I	SUPER CORR A or B; Lektrotech, Inc, 4302 Henderson Boulevard Suite 114, Tampa, Florida 33629, P.O. Box 18566 Zip 33679, (813) 254-1380; or 1006 CON-TAC; International Lubricants and Fuel Consultants (ILFC), 521 Quantum Road, Rio Rancho, New Mexico, 87124, (505) 892-1666; Both of these CPCs conform to MIL-L-87177A Grade B and have been tested in lab and field tests with excellent corrosion preventive results.

On page 10 replace the first 12 lines on the page with the following rewritten lines to delete the word "at" on line 6 following temperature to 200°F:

may quantitatively remove moisture in the cracks, holes and any surface imperfections. The saturated vapor line, the boiling point of water at different absolute pressures can be determined from the published "Steam Tables" (see Ellenwood et al., **Thermodynamic Charts**, John Wiley & Sons (1944), especially Tables 5B, 6A, or 6B). Table III presents water's boiling temperature at reduced, absolute, pressures from the Thermodynamic Charts. Reducing the pressure in the autoclave or vacuum chamber to 10-psia and elevating the temperature to 200° F may remove any remaining water within the surface cracks. When atmospheric pressure is restored to the surface of the metal the CPC may be driven further into the surface cracks or cavities, thus may provide a long term corrosion preventive treatment that may mitigate or prevent deeper crack penetrations, provide premium corrosion protection on the metal and at crack apexes. These treatments may result in increased metal strength, increased flexibility, and significantly increased fatigue life, all desirable phenomena.